

## Crazing-Resistant Engobe (EB101, EB102)

Crazing-Resistant Engobe has wide firing temperature range and are suitable for various applications, including wall tile, floor tile, rustic tile, whole cast glaze tile and etc.

This special engobe structure is induced by EB101/EB102 during firing process to enhance the crystalized structure at the interface of body and glaze, and further resist crazing between body and glaze after firing.

Application:

<b>EB-101/EB-102</b>	<b>70-85%</b>
<b>ZrSiO<sub>4</sub></b>	<b>0-10%</b>
<b>Clay</b>	<b>5-15%</b>
<b>Kaolin</b>	<b>10-20%</b>

Note:

1. EB-101 and EB-102 can be applied individually or blend together.
2. The ratio of kaolin and ball clay of the engobe formula is flexible according to the casting condition.
3. EB-101 and EB-102 can be applied with other feldspars or frits to meet different firing conditions

#### HEAD OFFICE

5F, No.27, Sec 1, Chang-an E. Rd.  
Zhongshan District, Taipei City 104,  
Taiwan (R.O.C)  
TEL: +886-2-25364771  
FAX: +886-2-25817391

#### LUNGTAN FACTORY, TAIWAN

No.11, Nan Wo Kou, Kao Ping  
Villiage, Lungtan Hsiang,  
Taoyuan County 325, Taiwan (R.O.C)  
TEL: +886-3-4716779  
FAX: +886-3-4718367

#### SANSHUI FACTORY, CHINA

Industrial Park, Lubao Town,  
Sanshui District, Foshan City,  
Guangdong Province 528139 China  
TEL: +86-757-87239929  
FAX: +86-757-87230100